

Available online at http://www.ijcrls.com

International Journal of Current Research in Life Sciences Vol. 07, No. 02, pp.1194-1197, February, 2018



# **RESEARCH ARTICLE**

# NANO ENCAPSULATION OF BERBERINE AND COLLAGEN 1

# \*Ganesan. Vijaiyan Siva and C. Surendra Babu

### Department of Biotechnology, Guindy campus, University of Madras, Chennai-25

Received 10<sup>th</sup> December, 2017; Accepted 13<sup>th</sup> January, 2018; Published Online 28<sup>th</sup> February, 2018

## ABSTRACT

Berberine has long been used as a traditional medicine because of its potential activity against Bacterial, fungal, viral diseases. Berberine have a complex and diverse chemical structure provide a base for different biological targets. The present study deals with the novel encapsulation of biopolymer called Collagen1 with berberine by Electrospinning method in different compositions, parameters, and method for preparation. By electrospinning not only we get desired mechanical and biological properties of encapsulation studies, but also used to combine these two different materials with wide range of drug delivery science and tissue engineering properties to produce electrospun nanofibres at different compositions. The physical and thermal properties of electro spun nanofibres interaction and were examines under FE-SEM. resultant studies may be used in variety of applications including Chemical, Genetical, Immunological and industrial purposes.

Key words: Nano encapsulation, Berberine, Collagen

**Copyright** © 2018, Ganesan. Vijaiyan Siva and Surendra Babu, C. This is an open access article distributed under the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Citation: Ganesan. Vijaiyan Siva and Surendra Babu, C. 2018. "Nano encapsulation of berberine and collagen 1" International Journal of Current Research in Life Sciences, 7, (02), 1194-1197.

# **INTRODUCTION**

Encapsulation studies were mainly useful for tissue engineering (Dechwisissakul, 2000) and meeting a wide range of applications in Biotechnology, Environmental, and Medicine fields (Ganesan, 2015). Mainly these studies made possible in nano particles engineering, which enhances the site specific drug delivery system and improves the pharmaco kinetics properties to drug (Namba, 1985). There are many methods to perform encapsulation studies, in this study we discuss abut electrospinning method. Electro spinning is a method which uses electrical energy as a source and fabricate fibres in different diameter ranges from microns to nano meters. Berberine is a plant alkaloid with many biological activities (Hattori, 1995). Preclinical in vitro and in vivo studies carry diverse pharmacological actions of berberine that could be potentially helpful in the management of infectious, anti-bacterial anti-inflamatory and metabolic diseases (Ray, 1976). To study more about we conducted the study in nanotechnology collagen by infusing berberine in (Rungsimakan, 2001) for drug delivery experiments for that we will get to know about encapsulation nature of drug. The purpose of this study is to identify the potential of drug by using electrospinning (Chang, 1964) at different compositions of berberine infused collagen.

## **MATERIALS AND METHODS**

#### **Collagen cross linking**

The collagen 1 was cross-linked (Lim, 1980) by dealing with glutaraldehyde vapor, soaked with 20% glutaraldehyde solution at room temperature for different time period (Löhr,, 1999), followed by treatment with 0.2M glycine aqueous solution to lump un reacted Amino acids (Löhr, 2001).

**Preparation of solutions:** Extracted (Lohr, 2003) collagen type I and the proteins were dissolved in HCL for 8 hours at room temperature. Whereas the berberine solution (Murua, 2008) was prepared by dissolving 50 mg of berberine in 2ml of methanol and then the emulsify (Sakai, 2005) it with 1% Pva solution and run in cyclo mixture for 2 hours to homogenise the solution. The mixture of berberine and collagen solutions were prepared (Cellesi, 2004) in the weight ratio of 1:2, 1:1, 2:1 for encapsulation.

**Parametres:** The electrospinnig instrument can be used for various solutions (Govan, 1981), but every solution has its own properties. To prepare the encapsulation (Otterlei, 1991) mainly we need ,Drum rotation speed, Syringe translation speed, Solution flow rate, Voltage required the following table has listed the parameters we used for encapsulation (Espevik, 1993). Preliminary experiments revealed that, independent of the conditions used, continuous fibres could not be spun from acidic aqueous solutions of pure collagen (Soon-Shiong, 1991).

<sup>\*</sup>Corresponding author: Ganesan. Vijaiyan Siva,

Department of Biotechnology, Guindy campus, University of Madras, Chennai-25



SEM Image of 2 parts of Berbenine and 1 part of collagen

SEM Image of 1 part collagen and 1 part berberine

SEM image of 2 part of collagen and 1part of berberine

It is known that by addition of sodium chloride to the solution, formation of fibres by electrospinning becomes possible due to the increase in solution conductivity . Moreover, the presence of NaCl can induce hydrophobic interactions (Clayton, 1991) in or between the protein molecules and thus contribute to the production of continuous fibres The higher net charge increases the force exerted on the jet and at a concentration of 42.5mM NaCl and spinning voltages between 10 and 25 kV, fibre formation was observed. However, continuous jets could not be produced and only short beaded fibres were obtained. This latter phenomenon is known to be favoured by the presence of a high electric field, which leads to capillary breakup of the electrospinning jet (Orive, 2006). Increasing the viscosity of the spinning solution is a way to overcome the formation of beads and a suitable polymer for this purpose we use PVA (De Vos, 1997). Addition of this polymer to the protein solution, which also contained 42.5mM NaCl, allowed a much better control over fibre formation. The voltages necessary to obtain a continuous fibre (De Vos, 1999) were dependent on the weight ratio of collagen to Berberine. Collagen and berberine solutions (Dusseault, 2006) (2% w/v) containing 42.5mM sodium chloride, having a collagen and berberine weight ratio of 1:2 and spun at 21 kV, afforded the formation of a continuous jet (Tam, 2006). However, the collected fibres were not completely dry and resulted in meshes of highly fused fibres. Increasing the weight ratio between collagen and Berberine (King, 2003) to 1:1 or 2:1 required higher potentials of 22 and 23.5 kV, respectively. However, at a collagen and berberine weight ratio of 1:2, beaded and highly fused fibres were obtained. Obviously, under these conditions (Strand, 2003) the water evaporation from the fibres was not complete. Dry fibres entirely devoid of beads and with a narrow diameter distribution (Boontheekul, 2008) (average fibre diameter 1/4 0.4070.05 mm) were produced at a weight ratio of collagen and berberine equal to 1:1.

**Electrospinning:** The electrospinning method consists (Orive, 2003) a syringe needle, electrode, stainless sheet paper on drum and electric supply. 5ml syringe filled with polymer solution which is linked to syringe pump. Solutions (Strand, 2001) will be hard pressed through tube on a rotating drum which is covered by stainless steel paper. The needle (distance between needle and rotate drum should be 6cm to collect the fibres) was associated (Calafiore, 1999) to high voltage supply (Maximum volts 40 kv and the experiment has to be carried at room temperature). The solution (Wang, 1997) will get a positive voltage which is 30 kv and the fibres were collected (Haque, 2005) on steel paper with the speed of 0.5 ml/hour

#### SEM

The resultant Microscopic images of different composition (Green, 2005) of polymer encapsulation (Chen, 2007) has viewed under FESEM-EXT-501 microscope.

#### RESULTS

Different compositions of Berberien and collagen mixtures (2:2, 1:1, 1:2) were performed to produce fibres from soluble berberine. As with collagen solutions, addition of NaCl at a concentration of 42.5mM and PVA at a concentration of 1% w/v were necessary to obtain a continuous fibres., it was possible to spin fibres at a voltage of 10 kV and a flow rate of 50 ml/ min. These fibres had an average thickness of 0.5 mm, The fibres have a rough surface and appear to be composed of 5-10nm wide filaments, oriented parallel to their longitudinal axis similarly to native elastin fibres As with collagen, the Berberine appear to preserve the ability to self organize into the native structure during fibre formation in the electrospinning process. The fibres were easily produced, but difficult to collect because of substantial splaying. Splaying occurs when the radial forces derived from the electrical charges carried by the jet, overcome the cohesive forces in the jet itself. The single jet divides into many charged jets before reaching the collecting plate. In the arterial wall, collagen and elastin are both present and constitute together with the extracellular matrix and the cells, a fibre-reinforced composite structure of which the mechanical properties are mainly determined by the fibrous network.

The presence of both proteins is necessary to confer the vessel its strength but also its elasticity. In the arterial wall, collagen and Berberine are both present and constitute together with the extracellular matrix and the cells, a fibre-reinforced composite structure of which the mechanical properties are mainly determined by the fibrous network. The presence of Both mixture concentrations is necessary to confer the vessel its strength but also its elasticity Aqueous solutions comprising collagen, Berberine (weight ratios are, 2:1, 1:1, 1:2) and The degree of cross linking was estimated by determining both the denaturation temperature and the residual amount of free amine groups of (non-)cross linked samples. Formation of crosslinks in the collagen/ Berberine spun matrices increased the denaturation temperature of the samples. As a consequence of crosslinking, the amount of free amino groups present in the samples decreased Independent of the weight ratio of collagen to Berberine, the relative percentage of free amino groups left after cross linking of the fibres was decreased to approximately

30% of the original value. Moreover, by means of SEM, it was verified that no NaCl crystals were present at the surface of the EDC/NHS crosslinking ... fibres after Crosslinked collagen/berberine scaffolds with different weight ratios (2:1, 1:1, 1:2,) of the two solutions were formed. In all cases, the formation of a confluent multi-layer of SMC, growing on top of each other was observed by means of histology The possibility to electrospin collagen and berberine solutions into fibres composed of a homogeneous blend of the two solutions can lead to the production of scaffolds with extraordinary properties, completely different from those observed in analogous mixtures of Solutions, for which the separate contributions can always be well distinguished. Evaluation of the specific interactions occurring in or between soluble collagen and soluble berberine and theoretically resulting in formation of collagenous fibrillar structures and aggregation of collagen and berberine might result in a better understanding of the potential of the application of collagen/berberine electrospun scaffolds in different fields, like tissue engineering. Further investigations are actually being performed in this direction.

#### Conclusion

Electrospinning was used as a successful technique to produce non-woven meshes from aqueous solutions of collagen type I and Berberine. In all cases, the addition of NaCl was necessary to spin homogeneous and continuous fibres. Composition of the solution, net charge density and applied electric field were parameters influencing the morphology of the obtained fibres. Spinning collagen/elastin solutions vielded meshes composed of fibres with diameters ranging from 220 to 600nm. Stable scaffolds were prepared by cross linking with EDC/NHS. After cross linking, scaffolds completely devoid of NaCl were obtained. SMCs were successfully cultured on cross linked scaffolds and a confluent layer of cells was observed after 14 days on the surface of the different meshes. One of the advantages of electrospinning aqueous solution of collagen and Berberine is the formation of scaffolds with high porosity and surface area, two essential requisites for tissue engineering. Electrospinning solutions of the two solutions separately from each other can also give the possibility to produce multilayered scaffolds with controlled morphology and/or mechanical properties. Moreover, in this study, it has been shown that fibres, in which the two solutions cannot be distinguished, can be electrospun from a mixture of collagen and Berberine. This may result in fibres with extraordinary mechanical properties, different from those observed in analogous mixtures of the insoluble solutions. Further investigations are currently being done in this direction.

# REFERENCES

- Boontheekul, T., Kong, H.J. Hsiong, S.X., Huang, Y.C. *et al.* 2008. "Quantifying the relation between bond number and myoblast proliferation". *Faraday Discussions* 139: 57–30. doi:10.1039/B719928G.
- Calafiore, R., Basta, G., Luca, G. *et al.* (June 1999). "Transplantation of pancreatic islets contained in minimal volume microcapsules in diabetic high mammalians". Annals of the New York Academy of Sciences 875: 219–32. doi:10.1111/j.1749-6632.1999.tb08506.x. PMID 10415570.
- Cellesi, F., Weber, W., Fussenegger, M., Hubbell, J.A., Tirelli, N. (December 2004). "Towards a fully synthetic substitute

of alginate: optimization of a thermal gelation/chemical cross-linking scheme ("tandem" gelation) for the production of beads and liquid-core capsules". Biotechnol. Bioeng. 88 (6): 740–9. doi:10.1002/bit.20264. PMID 15532084.

- Chang, T.M. (October 1964). "Semipermeable microcapsules". Science 146 (3643): 524–5. doi:10.1126/ science. 146.3643.524. PMID 14190240.
- Chen, H., Ouyang, W., Jones, M. *et al.* 2007. "Preparation and characterization of novel polymeric microcapsules for live cell encapsulation and therapy". Cell Biochem. Biophys. 47(1): 159–68. doi:10.1385/cbb:47:1:159. PMID 17406068
- Clayton, H.A., London, N.J., Colloby, P.S., Bell, P.R., James, R.F. 1991. "The effect of capsule composition on the biocompatibility of alginate-poly-l-lysine capsules". J Microencapsul 8 (2): 221–33. doi:10.3109/ 02652049109071490. PMID 1765902.
- De Vos, P., De Haan, B., Van Schilfgaarde, R. (February 1997). "Effect of the alginate composition on the biocompatibility of alginate-polylysine microcapsules". Biomaterials 18 (3): 273–8. doi:10.1016/S0142-9612(96)00135-4. PMID 9031730.
- De Vos, Paul; R. van Schifgaarde (September 1999). "Biocompatibility issues". In Kühtreiber, Willem M.; Lanza, Robert P.; Chick, William L. Cell Encapsulation Technology and Therapeutics. Birkhäuser Boston. ISBN 978-0-8176-4010-1.
- Dechwisissakul, P., Bavovada, R., Thonghoom, P., Maison, T. 2000. Pharmacognostic identification of Hamm. *Thai J Pharm Sci.*, 24(suppl): 31.
- Dusseault, J., Tam, S.K., Ménard, M. et al. February 2006). "Evaluation of alginate purification methods: effect on polyphenol, endotoxin, and protein contamination". J Biomed Mater Res A 76 (2): 243–51. doi:10.1002/jbm.a.30541. PMID 16265647.
- Espevik, T., Otterlei, M., Skjåk-Braek, G., Ryan, L., Wright, S.D., Sundan, A (January 1993). "The involvement of CD14 in stimulation of cytokine production by uronic acid polymers". *Eur. J. Immunol.* 23 (1): 255–61. doi:10.1002/eji.1830230140. PMID 7678226.
- Ganesan. Vijaiyan siva, C. Surendra. Babu 2015. "Targeting study of plant alkaloid Bereberine act as a natural drug inhibitor of Hsp90 (Heat shock proteins)". *International Journal of ChemTech Research*, Volume 7, No:5 PP 2130-2132, ISSN: 0974-4290
- Govan, J.R., Fyfe, J.A., Jarman, T.R. (July 1981). "Isolation of alginate-producing mutants of Pseudomonas fluorescens, Pseudomonas putida and Pseudomonas mendocina". J. Gen. Microbiol. 125 (1): 217–20. doi:10.1099/00221287-125-1-217. PMID 6801192.
- Green, D.W., Leveque, I., Walsh, D. *et al.* (April 2005). "Biomineralized polysaccharide capsules for encapsulation, organization, and delivery of human cell types and growth factors". *Advanced Functional Materials* 15 (6): 917–923. doi:10.1002/adfm.200400322.
- Haque, T., Chen, H., Ouyang, W. *et al.* (March 2005). "In vitro study of alginate-chitosan microcapsules: an alternative to liver cell transplants for the treatment of liver failure". Biotechnol. Lett. 27 (5): 317–22. doi:10.1007/s10529-005-0687-3. PMID 15834792.
- Hattori, M., Nakabayashi, T., Lim, Y. 1995. Inhibitory effect of various Ayuravedic and Panamanian medicinal plants on the infection of herpes simplex virus-I in vitro and in vivo. *Phytother Res*, 9:270–276.

- King, A., Strand, B., Rokstad, A.M. *et al.* March 2003. "Improvement of the biocompatibility of alginate/poly-llysine/alginate microcapsules by the use of epimerized alginate as a coating". *J Biomed Mater Res A* 64 (3): 533– 9. doi:10.1002/jbm.a.10276. PMID 12579568.
- Lim, F., Sun, A.M. (November 1980). "Microencapsulated islets as bioartificial endocrine pancreas". Science 210 (4472): 908–10. doi:10.1126/science.6776628. PMID 6776628.
- Löhr, M., Bago, Z.T., Bergmeister, H, Ceijna, M. Freund, M; Gelbmann, W; Günzburg, WH; Jesnowski, R; Hain, J; Hauenstein, K; Henninger, W; Hoffmeyer, A; Karle, P; Kröger, JC; Kundt, G; Liebe, S; Losert, U; Müller, P; Probst, A; Püschel, K; Renner, M; Renz, R; Saller, R; Salmons, B; Walter, I (April 1999). "Cell therapy using microencapsulated 293 cells transfected with a gene construct expressing CYP2B1, an ifosfamide converting enzyme, instilled intra-arterially in patients with advancedstage pancreatic carcinoma: a phase I/II study.". Journal of molecular medicine (Berlin, Germany) 77 (4): 393–8. doi:10.1007/s001090050366. PMID 10353444.
- Löhr, M., Hoffmeyer, A., Kröger, J., Freund, M., Hain, J., Holle, A., Karle, P., Knöfel, WT., Liebe, S., Müller, P., Nizze, H., Renner, M., Saller, RM., Wagner, T., Hauenstein, K., Günzburg, WH., Salmons, B (May 19, 2001). "Microencapsulated cell-mediated treatment of inoperable pancreatic carcinoma.". Lancet 357 (9268): 1591–2. doi: PMID 11377651.
- Lohr, M., Kroger, J-C., Hoffmeyer, A., Freund, M., Hain, J., Holle, A., Knofel, W. T., Liebe, S., Nizze, H., Renner, M.,Saller, R.; Karle, P.; Muller, P.; Wagner, T.; Hauenstein, K.; Salmons, B.; Gunzberg, W. H. 2003. "Safety, feasibility and clinical benefit of localized chemotherapy using microencapsulated cells for inoperable pancreatic carcinoma in a phase I/II trial". Cancer Therapy 1: 121–31.
- Murua, A., Portero, A., Orive, G., Hernández, R.M, de Castro M, Pedraz JL (December 2008). "Cell microencapsulation technology: towards clinical application". *J Control Release* 132 (2): 76–83. doi:10.1016/j.jconrel.2008.08.010. PMID 18789985.
- Namba, T., Tsunnezuka, M., Dissanayake, D.M.R.B. 1985. Studies on dental caries prevention by traditional medicines (part 3): Screeningof Ayuravedic medicines for anti-plaque action. Shoyakugaku Zasshi., 39: 146–153.
- Orive, G. Tam, S.K., Pedraz, J.L., Hallé, J.P. (July 2006). "Biocompatibility of alginate-poly-l-lysine microcapsules

for cell therapy". Biomaterials 27 (20): 3691–700. doi:10.1016/j.biomaterials.2006.02.048. PMID 16574222.

- Orive, G., Hernández, R.M., Gascón, A.R., *et al.* (January 2003). "Cell encapsulation: promise and progress". Nat. Med. 9 (1): 104–7. doi:10.1038/nm0103-104. PMID 12514721.
- Otterlei, M., Ostgaard, K., Skjåk-Braek, G., Smidsrød, O., Soon-Shiong, P., Espevik, T. (August 1991). "Induction of cytokine production from human monocytes stimulated with alginate". *J. Immunother.* 10 (4): 286–91. doi:10.1097/00002371-199108000-00007. PMID 1931864.
- Ray, P.G., Majumda, S.K. 1976. Antimicrobial activity of some Indian plants. Econ Bot., 30: 317–320.
- Rowley, J.A., Mooney, D.J. 2002. "Alginate type and RGD density control myoblast phenotype". *Journal of Biomedical Materials Research* 60 (2): 217–223. doi:10.1002/jbm.1287.
- Rungsimakan, S. 2001. Pharmacognostic Property of Khamin khruea; Master's thesis Graduate School, Chulalongkorn University.
- Sakai S, Kawabata K, Ono T, Ijima H, Kawakami K (August 2005). "Development of mammalian cell-enclosing subsieve-size agarose capsules (<100 microm) for cell therapy". Biomaterials 26 (23): 4786–92. doi:10.1016/j.biomaterials.2004.11.043. PMID 15763258.
- Soon-Shiong, P., Otterlie, M., Skjak-Braek, G., *et al.* (February 1991). "An immunologic basis for the fibrotic reaction to implanted microcapsules". Transplant. Proc. 23 (1 Pt 1): 758–9. PMID 1990681.
- Strand, B.L., Mørch, Y.A., Syvertsen, K.R., Espevik, T., Skjåk-Braek, G. (March 2003). "Microcapsules made by enzymatically tailored alginate". J Biomed Mater Res A 64 (3): 540–50. doi:10.1002/jbm.a.10337. PMID 12579569.
- Strand, B.L., Ryan, T.L., In't Veld P; *et al.* (2001). "Poly-lysine induces fibrosis on alginate microcapsules via the induction of cytokines". Cell Transplant 10 (3): 263–75. PMID 11437072.
- Tam, S.K., Dusseault, J., Polizu, S., Ménard, M., Hallé, J.P., Yahia, L. (March 2006). "Impact of residual contamination on the biofunctional properties of purified alginates used for cell encapsulation". *Biomaterials* 27 (8): 1296–305. doi:10.1016/j.biomaterials.2005.08.027. PMID 16154192.
- Wang, T., Lacík, I., Brissová, M. *et al.* (April 1997). "An encapsulation system for the immunoisolation of pancreatic islets". Nat. Biotechnol. 15 (4): 358–62. doi:10.1038/nbt0497-358. PMID 9094138.

\*\*\*\*\*\*